3K PLUS

Additive improving mechanical properties, scratch resistance and durability of PU FEST 2K polyurethane varnish.

APPLICATION



Mixing proportions of PU FEST 2K and 3KPLUS:

- 5 parts by weight of component A of PU FEST 2K
- 1 part by weight of component B of PU FEST 2K
- 0.5 part by weight of 3K PLUS
- then add 10% of water in relations to all components

Example: A + B + 3K PLUS = 5 + 1 + 0.5 (+ 10% water)

5 kg of component A + 1 kg of component B (mix) + 0.5 kg of component 3K PLUS (mix) + 10% of water (0.65 kg). Then mix everything thoroughly for about 2-3 minutes.

It is not recommended to add more than the recommended amount of 3K PLUS component.

SAFETY AND HEALTH

- Causes serious eye irritation.
- May cause drowsiness or dizziness.
- Frequent contact may cause skin dryness and cracking.
- If medical attention is needed, have the product container or label on hand.
- Keep out of reach of children.
- Keep container tightly closed.



- Use only outdoors or in a well-ventilated area.
- Wear protective gloves / protective clothing / eye protection / face protection.
- Contact a doctor if you feel unwell.
- Dispose of waste at special collection points.



PACKAGING

3K PLUS is delivered in 0.5 kg package.

TECHNICAL DATA

- Mixing proportion of PU FEST 2K and 3KPLUS: A+B+3K PLUS (+10% water)
- Color: milky
- Application temperature: from +15°C to +25°C
- Light foot traffic possible after 24 hours, full load after 7 days
- Open time: 45 minutes
- Shelf life: 12 months

